

**CERTIFICATE OF ANALYSIS****CERTIFICATE NO.** 1006387.115/1283**CUSTOMER**BioCote Ltd  
Wolverhampton Science Park  
Technology Centre  
Glaisher Drive  
Wolverhampton  
WV10 9RU**CUSTOMER REF.**

07/025

**SAMPLE DETAILS**

SILVERGUARD

**DATE RECEIVED**

23/01/2007

**ORDER NO.****METHOD: Determination of Antibacterial Activity using Test Based on JIS Z 2801: 2000****DATE ANALYSED** 24/01/2007**DATE REPORTED**

26/01/2007

**RESULTS (AS CFU CM<sup>-2</sup>)**

SAMPLE	SPECIES	CONTACT TIME		REDUCTION (INITIAL)	
		0 hrs	24 hrs	Log 10	%
SilverGuard with BioCote (TOWEL)	E coli	2.0E+04	1.8E+01	3.0	99.91%

The above data shows the change in population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95%

INDUSTRIAL MICROBIOLOGICAL SERVICES LTD  
PALE LANE  
HARTLEY WINTNEY  
HANTS  
RG27 8DH  
UKPeter D Askew  
Managing Director